

PLIXXENT HOLDING GMBH MITTELKAMP 112 OLDENBURG, 26125 Germany



Baydur 66 FR-1(z)

Polyurethane (PUR), multiple component system, foam

(z) - Multiple component system. Refer to manufacturers technical datasheets for information about mixing ratio and designation of individual components.

Flammability	Value	Test Method
Flame Rating		UL 94
4.0 mm, BK	V-0	IEC 60695-11-10, -20
5.8 mm, NC	V-0	
Thermal	Value	Test Method
RTI Elec		UL 746B
4.0 mm	50.0 °C	
5.8 mm	50.0 °C	
RTI Imp		UL 746B
4.0 mm	50.0 °C	
5.8 mm	50.0 °C	
RTI Str		UL 746B
4.0 mm	50.0 °C	
5.8 mm	50.0 °C	
Physical	Value	
Density Range	560 to 650 kg/m³	